

SURPLUSTRADERS.NET

PO Box 276
Alburg, VT 05440

Website: www.surplustraders.net
Email: ted@surplustraders.net

Tel: 514-739-8723
Fax: 514-345-8303

This spec sheet is provided courtesy of Surplustraders.net

If you are looking for brand names, model numbers or other products that are not currently represented in this spec sheet, please, give me a call or send me an email with your requirements so we can further discuss your needs.

Thank you
Ted Duskes

Ph: 514-739-8723

Fx: 514-345-8303

Email: ted@surplustraders.net

Website: www.surplustraders.net

Primary lithium batteries

LST 17330

3.6V Primary lithium-thionyl chloride (Li-SOCl₂)

High energy density

²/₃ A-size bobbin cell

For applications requesting good voltage response and operating life in -60°C/+85°C environments.



Key features

- High and stable operating voltage
- Low self-discharge rate
(less than 1% after 1 year of storage at +20°C)
- Hermetic glass-to-metal sealing
- Non-flammable electrolyte
- Compliant with IEC 86-4 safety standard and EN 50020 intrinsic safety standard
- Underwriters Laboratories (UL) Component Recognition (File Number MH 12802)
- Non-restricted for transport

Main applications

- Utility metering
- Automatic meter reading
- Alarms and security devices
- Tollgate systems
- Memory back-up
- Tracking systems
- Automotive electronics
- Professional electronics

etc...

Cell size reference

²/₃ A

Electrical characteristics

(typical values relative to cells stored for one year or less at +30°C max.)

Nominal capacity 2.1 Ah
(at 3 mA +20°C 2.0V cut off. The capacity restored by the cell varies according to current drain, temperature and cut off).

Open circuit voltage (at +20°C) 3.67V

Nominal voltage (at 0.2 mA +20°C) 3.6V

Pulse capability: Typically up to 120 mA (120 mA/0.1 second pulses, drained every 2 mn at +20°C from undischarged cells with 10 µA base current, yield voltage readings above 3.0V. The readings may vary according to the pulse characteristics, the temperature, and the cell's previous history. Fitting the cell with a capacitor may be recommended in severe conditions. Consult Saft)

Continuous current permitting 50% of the nominal capacity to be achieved at +20°C with 2.0V cut off. 25 mA
(Higher currents possible, consult Saft)

Storage (recommended) +30°C (+86°F) max
(for more severe conditions, consult Saft)

Operating temperature range -60°C/+85°C
(-76°F/+185°F)
(Operation above ambient T may lead to reduced capacity and lower voltage readings at the beginning of pulses. Consult Saft)

Physical characteristics

Diameter (max) 16.5 mm (0.65 in)

Height (max) 33.4 mm (1.31 in)


Typical weight 14.4 g (0.5 oz)

Li metal content approx. 0.6 g


Available termination suffix

CNR, CNR OP	rectangular radial tabs
2 PF, 3 PF, 3 PF RP	radial pins
CNA (AX)	axial leads


LST 17330




Dimensions in mm.



Voltage plateau versus Current and Temperature (at mid-discharge)



Typical discharge profiles at +20°C



Restored Capacity versus Current and Temperature (2.0V cut off)

Storage

- The storage area should be clean, cool (not exceeding +30°C), dry and ventilated.

Warning

- Fire, explosion and severe burn hazard.
- Do not recharge, short circuit, crush, disassemble, heat above 100°C (212°F), incinerate, or expose contents to water.
- Do not solder directly to the cell.

Saft

12, rue Sadi Carnot
93170 Bagnolet - France
Tel +33 1 49 93 19 18
Fax +33 1 49 93 19 69

River Drive, South Shields
Tyne & Wear, NE33 2TR - UK
Tel +44 191 456 1451
Fax +44 191 456 6383

www.saftbatteries.com

Doc. N° 31040-2-0904
Published by the Communications Department

Information in this document is subject to change without notice and becomes contractual only after written confirmation by Saft. For more details on primary lithium technologies please refer to Primary Lithium Batteries Selector Guide Doc N° 31048-2-0604. Photo credit: Saft. Produced by Arthur Associates

Société anonyme au capital de 31 944 000€
RCS Bobigny B 383 703 873

